

	Scheda Materiale Material Datasheet	Rev: 05
	Titanium	Page: 1/1
	Titanium grade 2	Date: May 2022

Denominazione del materiale:

Material designations:

EN	Ti grade 2
UNS	R50400
DIN	Ti 2 3.7035
AFNOR	T40

Utilizzo: NON IN CONTATTO DIRETTO E PROLUNGATO CON LA PELLE

Use: NOT IN DIRECT AND PROLONGED CONTACT WITH THE SKIN

Composizione chimica [wt.%]:

Chemical composition [wt.%]:

N	C	H	Fe	O	Ti	Other each	Other tot.
<0.03	<0.08	<0.015	<0.30	<0.25	balance	<0.1	<0.4

Proprietà fisiche: *

Physical properties: *

Densità Density	Resistività elettrica Electrical resistivity	Calore specifico Specific heat	Conducibilità termica Thermal conductivity	Modulo di elasticità Elastic modulus	Coeff. di espansione termica Coeff. of thermal expansion
ρ [kg/m ³]	ρ [$\mu\Omega\cdot m$]	c_p [J·kg ⁻¹ ·K ⁻¹]	λ [W·m ⁻¹ ·K ⁻¹]	E [Gpa]	α [10 ⁻⁶ /K]
4500	0.50	520	16÷22	105	8.4

*= a temperatura ambiente/reference values at room temperature

Proprietà meccaniche:

Mechanical properties:

	Carico di rottura Tensile strength	Carico di snervamento Yield strength	Allungamento Elongation	Durezza Hardness
	R _m [Mpa]	R _{p0.2} [Mpa]	A ₅ [%]	HV
From (annealed)	345	276	20÷22	140
To (half hard)	420	300	-	210

I valori indicati da questa scheda sono da considerarsi come media dei valori oggettivi rilevati dalla verifica periodica dei Certificati di Controllo della materia prima inviati dai fornitori a fronte di ciascuna partita approvigionata. A fronte delle informazioni rese disponibili dai fornitori o rilevate in proprio in modo controllato da apposita procedura interna, l'azienda si impegna ad aggiornare tempestivamente le informazioni contenute in questa scheda qualora intervengano variazioni oltre le tolleranze o i massimali già indicati per le sopra esposte caratteristiche, soprattutto riguardanti la composizione chimica della materia prima approvigionata.

The values on this Datasheet have to be considered as an average of the values registered by the regular examination of Inspection Documents supplied with each bath of raw material. The company contracts itself to promptly update the information of this Datasheet in case of changes over the tolerances or limits for the above-stated characteristics (especially for chemical composition), on the basis of the information given by suppliers or regularly verified by the company according to an appropriate internal procedure.